

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 260 546 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
27.11.2002 Bulletin 2002/48

(21) Application number: **01112368.4**

(22) Date of filing: **21.05.2001**

(51) Int Cl.⁷: **C08K 5/00, C08L 23/10,
F16L 9/12, F16L 9/127,
F16L 9/133, B32B 1/08,
B32B 27/32, C08F 110/06,
C08F 297/08, C08F 10/06**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(71) Applicant: **Borealis Technology OY**
06201 Porvoo (FI)

(72) Inventor: **The designation of the inventor has not
yet been filed**

(74) Representative: **VA TECH Patente GmbH & Co**
Stahlstrasse 21 a
4020 Linz (AT)

(54) **Polyolefin multilayer pipe**

(57) Polyolefin multilayer pipes consisting at least one of the layers of a β -nucleated propylene homopolymer and/or β -nucleated copolymers from 90.0 to 99.9 % by weight of propylene and 0.1 to 10.0 % by weight of α -olefins. The pipes are to be classified in ring stiffness class ≥ 4 .

The pipes are suitable for non pressure pipe appli-

cations, preferably for outdoor use, for above as well as underground drainage and sewerage pipe systems, surface water pipes, pipes for cable protection, pipes for cold climate conditions and for indoor use, soil and waste water pipes.

EP 1 260 546 A1

Description

Field of the invention

- 5 **[0001]** The invention relates to polyolefin multilayer pipes, fittings, chambers and the like wherein at least one of the layers comprises a β -nucleated propylene polymer, as well as a process for producing them.

Background of the invention

- 10 **[0002]** Polyolefin multilayer pipes wherein at least one of the layers of the multilayer pipe comprises a propylene polymer are known.
[0003] WO 98/43806 discloses a multilayer plastic tube, comprising a base tube consisting of a propylene polymer, a barrier layer coating the base tube, and a protective layer, containing a lubricant, applied on top of the barrier layer.
[0004] WO 97/33117 discloses a multilayer pipe with at least two layers of different plastic materials, in which one
 15 layer consists of a Ziegler-Natta propylene copolymer, optionally with 1-30 % by weight elastomer content.
[0005] The disadvantage of these multilayer pipes is the insufficient balance of high stiffness and good impact properties, especially at low temperatures.

Object of the invention


- 20 **[0006]** It is the object of the present invention to provide polyolefin multilayer pipes, where at least one of the layers of the multilayer pipe comprises a β -nucleated propylene polymer, with a superior combination of high stiffness and good impact properties, especially at low temperatures.

Brief description of the invention

- [0007]** According to the present invention, this object is achieved by polyolefin multilayer pipes where at least one of the layers of the multilayer pipe comprises a propylene homopolymer with melt indices of 0.05 to 10 g/10 min at 230°C/2.16 kg or propylene copolymers from 90.0 to 99.9% by weight of propylene and 0.1 to 10.0% by weight of α -olefins with 2 or 4 to 18 carbon atoms with melt indices of 0.05 to 15 g/10 min at 230°C/2.16 kg, or mixtures thereof,
 30 wherein the propylene homopolymers and/or propylene copolymers are β -nucleated propylene polymers and the multilayer pipe with a pipe diameter of less than 0.25 m has an impact energy E_D (normalised) of at least 400 Nm/m and a ring stiffness S determined according to ISO 9969 ≥ 4 kN/m² and a multilayer pipe with a pipe diameter of ≥ 0.25 m has an impact energy E of at least 120 Nm and a ring stiffness S determined according to ISO 9969 ≥ 4 kN/m².
 35 **[0008]** β -nucleated propylene polymers are isotactic propylene polymers composed of chains in a 3_1 helical conformation having an internal microstructure of β -form spherulites being composed of radial arrays of parallel stacked lamellae. This microstructure can be realized by the addition of β -nucleating agents to the melt and crystallization. The presence of the β -form can be detected through the use of wide angle X-ray diffraction (Moore, J., Polypropylene Handbook, p. 134-135, Hanser Publishers Munich 1996).
 40 **[0009]** According to an advantageous feature of the present invention the β -nucleated propylene polymers in at least one of the layers of the multilayer pipe are β -nucleated propylene homopolymers having an $IR_t > 0.98$, a tensile modulus of ≥ 1500 MPa at +23°C and a Charpy impact strength, using notched test specimens, at -20°C ≥ 3 kJ/m² and/or β -nucleated propylene block copolymers having an IR_t of the propylene homopolymer block of > 0.98 , a tensile modulus of ≥ 1100 MPa at +23°C and a Charpy impact strength ≥ 6 kJ/m² at -20°C using notched test specimens.
 45 **[0010]** The IR_t of the propylene polymers is measured by Infrared spectroscopy and calculated as described in EP 0 277 514 A2 on page 3.
[0011] The propylene homopolymers used in at least one layer of the multilayer pipe according to the present invention have melt indices of 0.05 to 15 g/10 min at 230°C/2.16 kg, preferably 0.1 to 8 g/10 min at 230°C/2.16 kg, most preferably 0.2 to 5 g/10 min at 230°C/2.16 kg.
 50 The propylene copolymers have melt indices of 0.05 to 20 g/10 min at 230°C/2.16 kg, preferably 0.1 to 8 g/10 min at 230°C/2.16 kg, most preferably 0.2 to 5 g/10 min at 230 °C/2.16 kg.
[0012] According to the present invention the propylene homopolymers used for at least one layer of the multilayer pipe show a tensile modulus ≥ 1500 MPa, preferably ≥ 1600 MPa and the propylene copolymers show a tensile modulus ≥ 1100 MPa, preferably ≥ 1300 MPa and most preferably ≥ 1500 MPa.
 55 **[0013]** The propylene homopolymers according to the present invention have a Charpy impact strength of ≥ 3 kJ/m² at -20°C, preferably 4 to 10 kJ/m² at -20°C, most preferably 5 to 10 kJ/m² at -20°C.
 The propylene copolymers according to the present invention have a Charpy impact strength of ≥ 6 kJ/m² at -20°C, preferably ≥ 9 kJ/m² at -20°C, most preferably ≥ 10 kJ/m² at -20°C. Charpy impact strength of up to at least 60 kJ/m² is

possible for copolymers used for the production of at least one layer of the multilayer pipe according to the invention.

[0014] According to a preferred embodiment of the present invention the β -nucleated propylene polymers with an $IR_T > 0.98$ in at least one of the layers of the multilayer pipe being propylene polymers obtained by polymerization with a Ziegler-Natta catalyst system comprising titanium-containing solid components, an organoalumina, magnesium or titanium compound as cocatalyst and an external donor according to the formula




wherein R and R' are identical or different and are branched or cyclic aliphatic or aromatic hydrocarbon residues, and y and x independently from each other are 0 or 1, provided that x + y are 1 or 2.

[0015] Example of propylene polymers with high stereospecificity obtained by polymerization with a Ziegler-Natta catalyst system, are propylene polymers as described in WO 99/24478 and WO 99/16797.

[0016] A preferred external donor in the Ziegler-Natta catalyst system for producing the propylene polymers with high stereospecificity comprised at least in one of the layers of the multilayer pipe is dicyclopentylmethoxysilane.

[0017] According to an advantageous embodiment of the present invention the β -nucleated propylene polymer contains 0.0001 to 2.0 wt%, based on the polypropylenes used,

- dicarboxylic acid derivative type diamide compounds from C₅-C₈-cycloalkyl monoamines or C₆-C₁₂-aromatic monoamines and C₅-C₈-aliphatic, C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic dicarboxylic acids, and/or
- diamine derivative type diamide compounds from C₅-C₈-cycloalkyl monocarboxylic acids or C₆-C₁₂-aromatic monocarboxylic acids and C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic diamines, and/or
- amino acid derivative type diamide compounds from amidation reaction of C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-arylamino acids, C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-aromatic monocarboxylic acid chlorides and
- quinacridone derivative compounds of the type quinacridone compounds, quinacridonequinone compounds, and/or dihydroquinacridone type compounds, and/or
- dicarboxylic acid salts of metals from group IIa of periodic system and/or mixtures of dicarboxylic acids and metals from group IIa of periodic system, and/or
- salts of metals from group IIa of periodic system and imido acids of the formula



wherein x = 1 to 4; R = H, -COOH, C₁-C₁₂-alkyl, C₅-C₈-cycloalkyl or C₆-C₁₂-aryl, and Y = C₁-C₁₂-alkyl, C₅-C₈-cycloalkyl or C₆-C₁₂-aryl - substituted bivalent C₆-C₁₂-aromatic residues, as β -nucleating agent.

[0018] Example of the dicarboxylic acid derivative type diamide compounds from C₅-C₈-cycloalkyl monoamines or C₆-C₁₂-aromatic monoamines and C₅-C₈-aliphatic, C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic dicarboxylic acids, optionally contained in the β -nucleated propylene polymers of at least one of the layers of the multilayer pipe, are

- N,N'-di-C₅-C₈-cycloalkyl-2,6-naphthalene dicarboxamide compounds such as N,N'-dicyclohexyl-2,6-naphthalene dicarboxamide and N,N'-dicyclooctyl-2,6-naphthalene dicarboxamide,
- N,N'-di-C₅-C₈-cycloalkyl-4,4-biphenyldicarboxamide compounds such as N,N'-dicyclohexyl-4,4-biphenyldicarboxamide and N,N'-dicyclopentyl-4,4-biphenyldicarboxamide,
- N,N'-di-C₅-C₈-cycloalkyl-terephthalamide compounds such as N,N'-dicyclohexylterephthalamide and N,N'-dicyclopentylterephthalamide,
- N,N'-di-C₅-C₈-cycloalkyl-1,4-cyclohexanedicarboxamide compounds such as N,N'-dicyclohexyl-1,4-cyclohexanedicarboxamide and N,N'-dicyclohexyl-1,4-cyclopentanedicarboxamide.

[0019] Example of the diamine derivative type diamide compounds from C₅-C₈-cycloalkyl monocarboxylic acids or C₆-C₁₂-aromatic monocarboxylic acids and C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic diamines, optionally contained in the β -nucleated propylene polymers of at least one of the layers of the multilayer pipe, are

- N,N',-C₆-C₁₂-arylene-bis-benzamide compounds such as N,N'-p-phenylene-bis-benzamide and N,N'-1,5-naphthalene-bis-benzamide,

- N,N'-C₅-C₈-cycloalkyl-bis-benzamide compounds such as N,N'-1,4-cyclopentane-bis-benzamide and N,N'-1,4-cyclohexane-bis-benzamide.
- N,N'-p-C₆-C₁₂-arylene-bis-C₅-C₈-cycloalkylcarboxamide compounds such as N,N'-1,5-naphthalene-bis-cyclohexanecarboxamide and N,N'-1,4-phenylene-bis-cyclohexanecarboxamide.
- N,N'-C₅-C₈-cycloalkyl-bis-cyclohexanecarboxamide compounds such as N,N'-1,4-cyclopentane-bis-cyclohexanecarboxamide and N,N'-1,4-cyclohexane-bis-cyclohexanecarboxamide.

[0020] Example of the amino acid derivative type diamide compounds, optionally contained in the β -nucleated propylene polymers of at least one of the layers of the multilayer pipe, are

N-phenyl-5-(N-benzoylamino)pentaneamide and/or
N-cyclohexyl-4-(N-cyclohexylcarbonylamino)benzamide.


[0021] Example of the quinacridone type compounds, optionally contained in the β -nucleated propylene polymers of at least one of the layers of the multilayer pipe, are quinacridone, dimethylquinacridone and/or dimethoxyquinacridone.

[0022] Example of the quinacridonequinone type compounds, optionally contained in the β -nucleated propylene polymers of at least one of the layers of the multilayer pipe, are quinacridonequinone, a mixed crystal of 5,12-dihydro (2,3b)acridine-7,14-dione with quino(2,3b)acridine-6,7,13,14-(5H,12H)-tetrone as disclosed in EP-B 0 177 961 and/or dimethoxyquinacridonequinone.

[0023] Example of the dihydroquinacridone type compounds, optionally contained in the β -nucleated propylene polymers of at least one of the layers of the multilayer pipe, are dihydroquinacridone, dimethoxydihydroquinacridone and/or dibenzodihydroquinacridone.

Example of the dicarboxylic acid salts of metals of group IIa of periodic system, optionally contained in the β -nucleated propylene polymers of at least one of the layers of the multilayer pipe, are pimelic acid calcium salt and/or suberic acid calcium salt.

[0024] Example of salts of metals from group IIa of periodic system and imido acids of the formula



are the calcium salts of phthaloylglycine, hexahydrophthaloylglycine, N-phthaloylalanine and/or N-4-methylphthaloylglycine.

[0025] A still further embodiment of the present invention is a 3-layer pipe, wherein the outer and inner layer of the pipe comprises a β -nucleated propylene polymer and the mid layer comprises a recycled propylene polymer, a propylene polymer of higher stiffness than the β -nucleated propylene polymer, and/or a propylene polymer containing fillers.

[0026] A still further embodiment of the present invention is a 2-layer pipe, wherein the outer layer of the pipe comprises a β -nucleated propylene polymer and the inner layer comprises a recycled propylene polymer, a propylene polymer of higher stiffness than the β -nucleated propylene polymer and/or a propylene polymer containing fillers.

[0027] Preferred propylene polymers of higher stiffness than the β -nucleated propylene polymer in the mid layer of the 3-layer pipe or in the inner layer of the 2-layer pipe are α -nucleated propylene homopolymers and/or copolymers from 90.0 to 99.9 % by weight of propylene and 0.1 to 10.0 % by weight of α -olefins with 2 or 4 to 18 carbon atoms.

[0028] Preferred α -nucleating agents, contained from 0.05 to 2 % by weight in the propylene polymers of higher stiffness, are dibenzylidene sorbitol, derivatives of sorbitol and/or diphenylglycine; salts of C₆-C₁₈ aliphatic or C₇-C₁₃ aromatic carbonic acids, selected from sodium benzoate, tert.-butylbenzoic acid alumina salt and/or long chain C₈-C₁₈-carbonic acid salts; phosphoric acid derivatives, selected from ammonium polyphosphate, cyclic calcium phosphate compounds, sodium-2,2'-methylenebis-(4,6-di-tert.-butylphenyl)phosphate and/or bis(tert.-butyl)-phosphoric acid sodium salt; and/or talc.

Further polymers of higher stiffness may be polymers different from isotactic propylene polymers, selected from the group of tetrafluoroethylene polymers, polycarbonates, polybutyleneterephthalate, polyethyleneterephthalate, 3-methyl-butene polymers, 4-methylpentene-1-polymers, syndiotactic propylene polymers, polyphenyleneoxides, propylene methylbutene copolymers, styrene acrylonitrile copolymers, poly-allyltrimethylsilanes and/or hydrolysed ethylene vinylacetate copolymers.

[0029] Preferred fillers contained in the propylene polymers of the mid layer of the 3-layer pipe or in the inner layer of the 2-layer pipe are Al_2O_3 , $\text{Al}(\text{OH})_3$, barium sulfate, calcium carbonate, glass beads, wood flour, silica, hollow microspheres, carbon black, talcum, bentonite, mica and/or wollastonite.

[0030] A further object of the present invention is a process for producing polyolefin multilayer pipes by extrusion or injection molding processes where at least one of the layers of the multilayer pipe comprises a propylene homopolymer with melt index of 0.05 to 10 g/10 min at 230°C/2.16 kg and/or copolymers from 90.0 to 99.9 % by weight of propylene and 0.1 to 10.0 % by weight of α -olefins with 2 or 4 to 18 carbon atoms with melt indices of 0.05 to 15 g/10 min at 230°C/2.16 kg, wherein the propylene homopolymers and/or propylene copolymers are β -nucleated propylene polymers.

[0031] In the production of polyolefin multilayer pipes according to the invention conventional extruders are suitable. For example, the polyolefin layers may be manufactured with single screw extruders with an L/D of 20 to 40 or twin screw extruders or other types of extruders, suitable for multilayer extrusion, as described for example in US 5,387,386 and FI 83184. Optionally, a melt pump and/or a static mixer can be used additionally between the extruder and the ring die head. Ring shaped dies with diameters ranging from approximately 20 to 2000 mm and even greater are possible. Advantageous die temperatures for discharging the melt are 180 to 240°C. After leaving the ring-shaped die, the polyolefin multilayer plastic pipes are taken off over a calibrating sleeve and cooled.

The multilayer pipe can also be manufactured in extrusion winding processes in diameters up to 3 to 4 meters or even larger.

The pipes may also be processed in corrugating devices in combination or close to the calibration step, for example for manufacturing of multilayer pipes of corrugated double/triple wall design with or without hollow sections or multilayer pipes with ribbed design.

[0032] The known methods of multilayer pipe extrusion or injection molding are described for instance, in Djordjevic, D., "Coextrusion", Rapra Review Reports, Vol. 6, No. 2, 1992, pp 51-53, or Plastic Extrusion technology, Hanser Publishers 1997, Chapter 3 (F. Hensen).

[0033] For producing the polyolefin multilayer pipes according to the invention, usual auxiliary materials e.g. 0.01 to 2.5 wt% stabilizers, 0.01 to 1 wt% processing aids, 0.1 to 1 wt% antistatic agents and 0.2 to 3 wt% pigments, in each case based on the olefin polymers used, may be used.

[0034] As stabilizers preferably mixtures of 0.01 to 0.6 wt% phenolic antioxidants, 0.01 to 0.6 wt% 3-arylbenzofuranones, 0.01 to 0.6 wt% processing stabilizers based on phosphites, 0.01 to 0.6 wt% high temperature stabilizers based on disulfides and thioethers and/or 0.01 to 0.8 wt% sterically hindered amines (HALS) are suitable.

[0035] According to a feature of the present invention the β -nucleated propylene polymers for use in at least one layer of the multilayer pipe are propylene polymers produced by melt mixing propylene homopolymers and/or propylene copolymers with 0.01 to 2.0 % by weight, based on the polypropylenes used, β -nucleating agents at temperatures from 175 to 250°C.

[0036] Preferred applications of polyolefin multilayer pipes are non pressure pipe applications, preferably for outdoor use, for above as well as underground drainage and sewerage pipe systems, surface water pipes, pipes for cable protection, pipes for cold climate conditions and for indoor use, soil and waste water pipes.

[0037] The advantage of the polyolefin multilayer pipes according to the invention is the possibility to produce tailor-made polyolefin pipes, fittings, chambers and the like with a superior combination of high stiffness and good impact properties, especially at low temperatures. The layer of β -nucleated propylene polymer allows thinner pipe walls of the polyolefin multilayer pipes, utilizing larger amounts of high stiffness propylene polymers in the mid layers, and using larger amounts of recycled propylene polymers and fillers in the mid layers.

[0038] For practical testing of the impact resistance, the pipes were subjected to external blows by the staircase method according to EN 1411. In this test, a series of the polyolefin multilayer pipes were conditioned at 0°C and subjected to a hammer with a striker type d 90 falling from different heights. As a result, $H_{50} [=m]$ indicates the height, at which 50 % of the pipes fail.

The energy E of the striker is calculated according to the formula

$$E = m \cdot g \cdot H_{50}$$

wherein m is the mass of the striker in kg (normally between 4 and 12.5 kg) and g is the gravitational acceleration (9.81 m/s²) and H_{50} is the height in meter from which the striker is dropped, when 50 % of the pipes fail.

The energy E_D normalized for different pipe diameters can be calculated as the energy E divided by the outer diameter of the pipe (in meter).

[0039] For pipes with outer diameters of less than 0.25 m it is desirable that the impact energy E_D is at least 400 Nm/m, preferably $\geq 600 \text{ Nm/m}$, more preferably $\geq 800 \text{ Nm/m}$, most preferably $\geq 1000 \text{ Nm/m}$.

[0040] For pipes with outer diameters of $\geq 0.25 \text{ m}$ the pipe dimensions are normally relatively thinner and it is desirable

that the energy E is at least 120 Nm, preferably ≥ 180 Nm, more preferably ≥ 240 Nm and most preferably ≥ 300 Nm. Ring stiffness tests have been performed according to ISO 9969 at +23°C. According to the thus determined ring stiffness values the pipes may be classified in ring stiffness classes which are 2, 4, 8, 10, 16, 20 etc. Pipes according to the invention will be classified at least as ring stiffness class 4.

Examples

[0041] The following tests were made using injection molded test specimen prepared according to ISO 1873
Tensile modulus according to ISO 527 (cross head speed 1 mm/min) at +23°C
Charpy impact strength, notched, according to ISO 179/1eA
Impact resistance according to EN 1411 (staircase method, striker d 90, H₅₀-value at 0°C/4.0 kg)
Ring stiffness according to ISO 9969 at +23°C

Example 1

1.1 Preparation of the β -nucleated propylene polymer

[0042] A mixture of
90 wt% of a propylene block copolymer, obtained by combined bulk and gas phase polymerization using a Ziegler-Natta catalyst system with dicyclopentylidimethoxysilane as external donor, having an ethylene content of 8.3 wt%, an IRT of the propylene homopolymer block of 0.985 and a melt index of 0.30 g/10 min at 230°C/2.16 kg,
10% by weight of a master batch comprising 99 parts by weight of a propylene block copolymer having an ethylene content of 8.3 wt%, an IRT of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 1 part by weight of pimelic acid calcium salt, and 0.1 wt% calcium stearate, 0.1 wt% tetrakis[methylene (3,5-di-t-butylhydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-t-butylphenyl)phosphite, based on the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of 100/145/185/210/220/225/225/220/200/185°C, homogenized, discharged and pelletized.
The resulting polypropylene polymer has a melt index of 0.32 g/10 min at 230°C/2.16 kg, a tensile modulus of 1290 MPa and a Charpy impact strength, using notched test specimens, at -20°C of 39 kJ/m².

1.2 Manufacture of the polyolefin 2-layer pipe

[0043] For manufacturing the polyolefin multilayer pipes, a conventional pipe extruder having a screw diameter of 60 mm, L/D=28, and one conventional side extruder having a screw diameter of 50 mm, all connected to a multilayer tool of conventional design, having the possibility of extruding 1-3 layers of varying thickness of the materials and composition of the layers, was used. The pipes were calibrated and cooled by means of a conventional downstream equipment.
For producing the 2-layer pipe, the 60 mm extruder (temperature profile 200/230/230/230/230/230/210/210°C) for the inner layer was fed with a recycled mixed propylene polymer (melt index 0.5 g/10 min at 230°C/2.16 kg), and a 50 mm side extruder (temperature profile 180/200/225/225/210°C) for the outer layer was fed with the β -nucleated propylene polymer of 1.1.

1.2.1.

[0044] The resulting 2-layer pipe, produced at a line speed of 1.1 m/min, has an outer diameter of 110 mm and an wall thickness of 5.2 mm. Thickness of the outer layer was 1.9 mm and of the inner layer 3.3 mm. Energy E_D was ≥ 1070 Nm/m and ring stiffness was 11.7 kN/m².

1.2.2.

[0045] A further 2 layer pipe, produced at a line speed of 1.1 m/min has an outer diameter of 110 mm and a wall thickness of 4.1 mm. Thickness of the outer layer was 1.0 mm and of the inner layer 3.1 mm. Energy E_D was ≥ 620 Nm/m and ring stiffness was 6 kN/m².

1.2.3

[0046] A further 2 layer pipe, produced at a line speed of 1.1 m/min has an outer diameter of 110 mm and a wall thickness of 3.5 mm. Thickness of the outer layer was 1.0 mm and of the inner layer 2.5 mm.

Energy E_D was ≥ 470 Nm/m and ring stiffness was 4.2 kN/m².

Example 2

2.1 Preparation of the β -nucleated propylene polymer

[0047] A mixture of

94 wt% of a propylene homopolymer, obtained by bulk polymerization using a Ziegler-Natta catalyst system with dicyclopentylmethoxysilane as external donor, having an IR_t of 0.985 and a melt index of 0.2 g/10 min at 230°C/2.16 kg, 6 wt% of a master batch comprising 99.8 parts by weight of a propylene block copolymer having an ethylene content of 8.3 % by weight, an IR_t of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 0.2 parts by weight of a mixed crystal of 5,12-dihydro(2,3b)acridine-7,14-dione with quino(2,3b)acridine-6,7,13,14-(5H,12H)tetrone, and 0.05 wt% magnesium stearate, 0.1 wt% tetrakis[methylene(3,5-di-t-butyl-hydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-t-butyl-phenyl)-phosphite, based on the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of 100/145/190/215/225/230/230/215/205/190°C, homogenized, discharged and pelletized.

The resulting polypropylene polymer has a melt index of 0.22 g/10 min at 230°C/2.16 kg, a tensile modulus of 1335 MPa and a Charpy impact strength, using notched test specimens, at -20°C of 35 kJ/m².

2.2 Manufacture of the polyolefin multilayer pipe

[0048] For producing the 3-layer pipe, the pipe extruder of 1.2 was used. The 60 mm extruder (temperature profile 200/230/230/230/230/230/210/210°C) for the intermediate layer was fed with a blend of 70 % by weight of a block propylene-ethylene copolymer (melt index 0.5 g/10 min at 230°C/2.16 kg, 4.2 % by weight of ethylene) and 30 % by weight of talcum, and both 50 mm side extruders (temperature profile 180/200/225/225°C) for the inner and outer layer were fed with the β -nucleated propylene polymer of 2.1. The resulting 3-layer pipe, produced at a line speed of 1.0 m/min, has an outer diameter of 110 mm and an wall thickness of 3.8 mm. The thickness of the outer layer was 1.0 mm, of the intermediate layer 1.8 mm and of the inner layer 1.0 mm.

Energy E_D was ≥ 1070 Nm/m and ring stiffness was 8.1 kN/m².

Example 3

3.1 Preparation of the β -nucleated propylene polymer

[0049] A mixture of

75 wt% of a propylene block copolymer obtained by combined bulk and gas phase polymerization using a Ziegler-Natta catalyst system with dicyclopentylmethoxysilane as external donor, having an ethylene content of 8.3 wt%, an IR_t of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at 230°C/2.16 kg, 25 wt% of a master batch comprising 99.5 parts by weight of a propylene block copolymer having an ethylene content of 8.3 wt%, an IR_t of the propylene homopolymer block of 0.985 and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 0.5 parts by weight of hexahydrophthaloylglycine calcium salt, and 0.1 wt% calcium stearate, 0.1 wt% tetrakis[methylene(3,5-di-t-butylhydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-t-butylphenyl)phosphite, based on the sum of the propylene polymers used, is melted in twin screw extruder with a temperature profile of 100/145/185/210/220/225/225/200/185°C, homogenized, discharged and pelletized.

The resulting polypropylene polymer has a melt index of 0.32 g/10 min at 230°C/2.16 kg, a tensile modulus of 1310 MPa and a Charpy impact strength, using notched test specimens, at -20°C of 37 kJ/m².

3.2. Manufacture of the polyolefin multilayer pipe

[0050] For producing the 2-layer pipe, the pipe extruder of 1.2 was used. The 60 mm extruder (temperature profile 200/230/230/230/230/210°C) for the inner layer was fed with a random propylene-ethylene copolymer (melt index 0.25 g/10 min at 230°C/2.16 kg, 3.5 % by weight of ethylene), and the 50 mm side extruder (temperature profile 180/200/225/225/210°C) for the outer layer was fed with the β -nucleated propylene polymer of 3.1.

The resulting 2-layer pipe, produced at a line speed of 1.6 m/min, has an outer diameter of 110 mm and an wall thickness of 5.0 mm. The thickness of both layers was 2.5 mm.

Energy E_D was ≥ 1070 Nm/m and ring stiffness was 10.1 kN/m².

Example 44.1 Preparation of the β -nucleated propylene polymer

[0051] A mixture of

93 wt% of a propylene homopolymer, obtained by bulk polymerization using a Ziegler-Natta catalyst system with dicyclopentylmethoxysilane as external donor, having an IR_t of 0.985 and a melt index of 0.2 g/10 min at 230°C/2.16 kg, 7 wt% of a master batch comprising 99.8 parts by weight of a propylene block copolymer having an ethylene content of 8.3 % by weight, an IR_t of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 0.2 parts by weight of a mixed crystal of 5,12-dihydro(2,3b)acridine-7,14-dione with quino(2,3b)acridine-6,7,13,14-(5H,12H)tetrone, and 0.05 wt% magnesium stearate, 0.1 wt% tetrakis[methylene(3,5-di-t-butyl-hydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-t-butyl-phenyl)-phosphite, based on the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of 100/145/190/215/225/230/230/215/205/190°C, homogenized, discharged and pelletized.

[0052] The resulting polypropylene polymer has a melt index of 0.22 g/10 min at 230°C/2.16 kg, a tensile modulus of 1340 MPa and a Charpy impact strength, using notched test specimens, at -20°C of 36 kJ/m².

4.2 Manufacture of the polyolefin multilayer pipe

[0053] For producing the 3-layer pipe, the pipe extruder of 1.2 was used. The 60 mm extruder (temperature profile 200/230/230/230/230/210/210°C) for the intermediate layer was fed with a blend of 70 % by weight of a block propylene-ethylene copolymer (melt index 0.5 g/10 min at 230°C/2.16 kg, 4.2 % by weight of ethylene) and 30 % by weight of talcum, and both 50 mm side extruders (temperature profile 180/200/225/225°C) for the inner and outer layer were fed with the β -nucleated propylene polymer of 4.1.

4.2.1

[0054] The resulting 3-layer pipe, produced at a line speed of 1.0 m/min, has an outer diameter of 110 mm and a wall thickness of 5.0 mm. The thickness of the outer layer was 1.0 mm, of the intermediate layer 3.0 mm and of the inner layer 1.0 mm. Energy E_D was ≥ 1070 Nm/m and ring stiffness was 17.0 kN/m².

4.2.2

[0055] A further 3-layer pipe, produced at a line speed of 1.0 m/min, has an outer diameter of 110 mm and a wall thickness of 3.8 mm. Thickness of the outer layer was 0.5 mm, of the intermediate layer 2.8 mm and of the inner layer 0.5 mm. Energy E_D was ≥ 440 Nm/m and ring stiffness was 8.5 kN/m².

Example 55.1. Preparation of the β -nucleated propylene polymer

[0056] A mixture of

75 wt% of a propylene block copolymer obtained by combined bulk and gas phase polymerization using a Ziegler-Natta catalyst system with dicyclopentylmethoxysilane as external donor, having an ethylene content of 8.3 wt%, an IR_t of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at 230°C/2.16 kg, 25 wt% of a master batch comprising 99.5 parts by weight of a propylene block copolymer having an ethylene content of 8.3 wt%, an IR_t of the propylene homopolymer block of 0.985 and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 0.5 parts by weight of hexahydrophthaloylglycine calcium salt, and 0.1 wt% calcium stearate, 0.1 wt% tetrakis[methylene(3,5-di-t-butylhydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-t-butylphenyl)phosphite, based on the sum of the propylene polymers used, is melted in twin screw extruder with a temperature profile of 100/145/185/210/220/225/225/200/185°C, homogenized, discharged and pelletized.

The resulting polypropylene polymer has a melt index of 0.32 g/10 min at 230°C/2.16 kg, a tensile modulus of 1310 MPa and a Charpy impact strength, using notched test specimens, at -20°C of 37 kJ/m².

5.2. Manufacture of the polyolefin multilayer pipe

[0057] For producing the 2-layer pipe, the pipe extruder of 1.2 was used. The 60 mm extruder (temperature profile 200/230/230/230/230/210°C) for the inner layer was fed with a mixture of 70 % random propylene-ethylene copolymer (melt index 0.25 g/10 min at 230°C/2.16 kg, 3.5 % by weight of ethylene), with 30 % talc and the 50 mm side extruder (temperature profile 180/200/225/225/210°C) for the outer layer was fed with the β -nucleated propylene polymer of 3.1.

[0058] The resulting 2-layer pipe, produced at a line speed of 1.6 m/min, has an outer diameter of 110 mm and an wall thickness of 4.2 mm. The thickness of both layers was 2.1 mm.

Energy E_D was ≥ 1070 Nm/m and ring stiffness was 9.9 kN/m².

Example 6

6.1 Preparation of the β -nucleated propylene polymer

[0059] A mixture of 95 wt% of a propylene homopolymer, obtained by bulk phase polymerization using a Ziegler-Natta catalyst system with dicyclopentylmethoxysilane as external donor, having an IR_t of 0.987 and a melt index of 1.1 g/10 min at 230°C/2.16 kg,

5 wt% of a master batch comprising 97.5 parts by weight of a propylene homopolymer having an IR_t of 0.987 and a melt index of 4.2 g/10 min at 230°C/2.16 kg, and 2.5 parts by weight of N,N'-dicyclohexyl-2,6-naphthalenedicarboxamide and 0.05 wt% calcium stearate, 0.1 wt% tetrakis[methylene(3,5-di-*t*-butylhydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-*t*-butylphenyl)-phosphite, based on the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of 100/145/190/215/225/205/190°C, homogenized, discharged and pelletized.

[0060] The resulting polypropylene polymer has a melt index of 1.2 g/10 min at 230°C/2.16 kg, a tensile modulus of 1765 MPa and a Charpy impact strength, notched, of 5.5 kJ/m² at -20°C.

6.2. Manufacture of the polyolefin multilayer pipe

[0061] For producing the 3-layer pipe, the pipe extruder of 1.2 was used. The 60 mm extruder (temperature profile 200/230/230/230/230/230/210/210°C) for the intermediate layer was fed with a blend of 70 % by weight of a propylene homopolymer (melt index 0.8 g/10 min at 230°C/2.16 kg, 4.2 % by weight of ethylene) and 30 % by weight of talcum, and both 50 mm side extruders (temperature profile 180/200/225/225°C) for the inner and outer layer were fed with the β -nucleated propylene polymer of 6.1.

6.2.1

[0062] The resulting 3-layer pipe, produced at a line speed of 1.0 m/min, has an outer diameter of 110 mm and a wall thickness of 5.0 mm. The thickness of the outer layer was 1.0 mm, of the intermediate layer 3.0 mm and of the inner layer 1.0 mm.

Energy E_D was ≥ 490 Nm/m and ring stiffness was 21.5 kN/m².

6.2.2

[0063] A further 3-layer pipe, produced at a line speed of 1.0 m/min, has an outer diameter of 110 mm and a wall thickness of 4.2 mm. Thickness of the outer layer was 0.7 mm, of the intermediate layer 2.7 mm and of the inner layer 0.8 mm.


Energy E_D was ≥ 420 Nm/m and ring stiffness was 12.2 kN/m².

Claims

1. Polyolefin multilayer pipes where at least one of the layers of the multilayer pipe comprises a propylene homopolymer with melt indices of 0.05 to 10 g/10 min at 230 °C/2.16 kg or a propylene copolymer from 90.0 to 99.9 % by weight of propylene and 0.1 to 10.0 % by weight of α -olefins with 2 or 4 to 18 carbon atoms with melt indices of 0.05 to 15 g/10 min at 230°C/2.16 kg, or mixtures thereof, wherein the propylene homopolymer and/or propylene copolymer are β -nucleated propylene polymers and the multilayer pipe with a pipe diameter of less than 0.25 m has an impact energy E_D (normalised) of at least 400 Nm/m and a ring stiffness S determined according to ISO 9969 ≥ 4 kN/m² and a multilayer pipe with a pipe diameter of ≥ 0.25 m has impact energy E of at least 120 Nm and


a ring stiffness S determined according to ISO 9969 ≥ 4 kN/m².

2. Polyolefin multilayer pipes according to claim 1 wherein the multilayer pipe with a pipe diameter of less than 0.25 m has an impact energy E_D (normalised) of at least 600 Nm/m and a ring stiffness S determined according to ISO 9969 ≥ 4 kN/m² and a multilayer pipe with a pipe diameter of ≥ 0.25 m has impact energy E of at least 180 Nm and a ring stiffness S determined according to ISO 9969 ≥ 4 kN/m².
3. Polyolefin multilayer pipe according to claim 1, wherein the β -nucleated propylene polymers in at least one of the layers of the multilayer pipe are β -nucleated propylene homopolymers having an $IR\tau > 0.98$, a tensile modulus of > 1500 MPa at $+23^\circ\text{C}$ and a Charpy impact strength, using notched test specimens, at $-20^\circ\text{C} \geq 3$ kJ/m² and/or β -nucleated propylene block copolymers having an $IR\tau$ of the propylene homopolymer block of > 0.98 , a tensile modulus of ≥ 1100 MPa at $+23^\circ\text{C}$ and a Charpy impact strength > 6 kJ/m² at -20°C using notched test specimens.
4. Polyolefin multilayer pipe according to one of the claims 1 to 3, wherein the β -nucleated propylene polymers with an $IR\tau > 0.98$ are propylene polymers obtained by polymerization with a Ziegler-Natta catalyst system comprising titanium-containing solid components, an organoalumina, magnesium or titanium compound as cocatalyst and an external donor according to the formula



wherein R and R' are identical or different and are branched or cyclic aliphatic or aromatic hydrocarbon residues, and y and x independently from each other are 0 or 1, provided that x + y are 1 or 2.

5. Polyolefin multilayer pipe according to claim 4, wherein the external donor is dicyclopentyl dimethoxysilane.
6. Polyolefin multilayer pipe according to one of claims 1 to 5, wherein the β -nucleated propylene polymer contains 0.0001 to 2.0 wt%, based on the polypropylenes used,
 - dicarboxylic acid derivative type diamide compounds from C_5 - C_8 -cycloalkyl monoamines or C_6 - C_{12} -aromatic monoamines and C_5 - C_8 -aliphatic, C_5 - C_8 -cycloaliphatic or C_6 - C_{12} -aromatic dicarboxylic acids, and/or
 - diamine derivative type diamide compounds from C_5 - C_8 -cycloalkyl monocarboxylic acids or C_6 - C_{12} -aromatic monocarboxylic acids and C_5 - C_8 -cycloaliphatic or C_6 - C_{12} -aromatic diamines, and/or
 - amino acid derivative type diamide compounds from amidation reaction of C_5 - C_8 -alkyl-, C_5 - C_8 -cycloalkyl- or C_6 - C_{12} -arylamino acids, C_5 - C_8 -alkyl-, C_5 - C_8 -cycloalkyl- or C_6 - C_{12} -aromatic monocarboxylic acid chlorides and C_5 - C_8 -alkyl-, C_5 - C_8 -cycloalkyl- or C_6 - C_{12} -aromatic monoamines, and/or
 - quinacridone derivative compounds of the type quinacridone compounds, quinacridonequinone compounds, and/or dihydroquinacridone type compounds, and/or
 - dicarboxylic acid salts of metals from group IIa of periodic system and/or mixtures of dicarboxylic acids and metals from group IIa of periodic system, and/or
 - salts of metals from group IIa of periodic system and imido acids of the formula



wherein x = 1 to 4; R = H, -COOH, C_1 - C_{12} -alkyl, C_5 - C_8 -cycloalkyl or C_6 - C_{12} -aryl, and Y = C_1 - C_{12} -alkyl, C_5 - C_8 -cycloalkyl or C_6 - C_{12} -aryl - substituted bivalent C_6 - C_{12} -aromatic residues, as β -nucleating agent.

7. Polyolefin multilayer pipe according to one of claims 1 to 6, wherein the multilayer pipe is a 3-layer pipe, wherein the outer and inner layer of the pipe comprises a β -nucleated propylene polymer and the mid layer comprises a recycled propylene polymer, a propylene polymer of higher stiffness than the β -nucleated propylene polymer, a propylene polymer containing fillers.
8. Polyolefin multilayer pipe according to one of claims 1 to 7, wherein the multilayer pipe is a 2-layer pipe, wherein the outer layer of the pipe comprises a β -nucleated propylene polymer and the inner layer comprises a recycled

propylene polymer, a propylene polymer of higher stiffness than the β -nucleated propylene polymer, a propylene polymer containing fillers.

- 5 9. Polyolefin multilayer pipe according to one of the claims 1 or 8, **characterized in that** the multilayer pipe is a smooth pipe with or without hollow sections.
- 10 10. Polyolefin pipe according to one of the claims 1 or 9, **characterized in that** the multilayer pipe is a corrugated or ribbed pipe with or without hollow sections.
- 15 11. A process for producing polyolefin multilayer pipes by extrusion or injection molding processes where at least one of the layers of the multilayer pipe comprises a propylene homopolymer with melt index of 0.05 to 10 g/10 min at 230°C/2.16 kg and/or copolymers from 90.0 to 99.9 wt% of propylene and 0.1 to 10.0 wt% of α -olefins with 2 or 4 to 18 carbon atoms with melt indexes of 0.1 to 15 g/10 min at 230°C/2.16 kg, wherein the propylene homopolymers and/or propylene copolymers are β -nucleated propylene polymers.
- 20 12. A process for producing polyolefin multilayer pipes of claim 11, wherein β -nucleated propylene polymers are propylene polymers produced by melt mixing propylene homopolymers and/or propylene copolymers with 0.0001 to 2.0 % by weight, based on the polypropylenes used, β -nucleating agents at temperatures from 175 to 250°C.
- 25 13. Use of polyolefin multilayer pipes of any one of claims 1 to 10 for non pressure pipe applications, preferably for outdoor use, for above as well as underground drainage and sewerage pipe systems, surface water pipes, pipes for cable protection, pipes for cold climate conditions and for indoor use, soil and waste water pipes.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 11 2368

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 99 40151 A (BERNREITNER KLAUS ;KONRAD ROLAND (AT); EBNER KARL (AT); PCD POLYME) 12 August 1999 (1999-08-12)	11	C08K5/00 C08L23/10 F16L9/12
A	* page 2, line 20-22; claims 1,2; example 1 *	12	F16L9/127 F16L9/133
Y		1,6,9,13	B32B1/08
Y		5,9,12	B32B27/32 C08F110/06 C08F297/08 C08F10/06
Y	WO 99 24479 A (BOREALIS AS ;JAEESKELAEINEN PIRJO (FI); MALM BO (FI); HUOVINEN PA) 20 May 1999 (1999-05-20) * claims 1,3,13-15,22,24,25,31,32,36-41 *	1-6,13	
Y	EP 0 714 923 A (SHOWA DENKO KK) 5 June 1996 (1996-06-05)	1-4,11,13	
A	* page 7, line 48 - page 8, line 5; claims; examples; tables *	7,8	
A	DE 297 22 949 U (PCD POLYMER GMBH) 9 April 1998 (1998-04-09) * page 2, paragraph 2 - page 3, paragraphs 3-5; claims 1-3,5; table 2 *	1-4,6,9,10,13	
D,Y	EP 0 177 961 A (DANUBIA PETROCHEMIE) 16 April 1986 (1986-04-16) * page 2, paragraph 3 - page 5-6, paragraph 2; claims 1,4; table 3 *	11,12	C08K C08L F16L B32B C08F
A	* page 7, paragraph 1 *	1,6	
A	US 6 051 638 A (GRABOW STAN ALLAN ET AL) 18 April 2000 (2000-04-18) * column 2, line 5-10-38 - column 3, line 36-38; claims 1,4 *	1,4,12,13	
		-/--	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 31 October 2001	Examiner Derz, T
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/02 (P.4/01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 11 2368

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.7)
A	WO 99 35430 A (BERNREITNER KLAUS ;BOREALIS AG (AT); KONRAD ROLAND (AT); EBNER KAR) 15 July 1999 (1999-07-15)	1-6	
Y	* page 2, line 7-10 - page 3, line 3; claims 1,5,7 * * page 7, line 3,4 - page 8, paragraphs 1-3; examples 1-6; table 2 *	11,13	
A	EP 0 790 262 A (CHISSO CORP) 20 August 1997 (1997-08-20) * page 8, line 50 - page 18, line 56; claims 1,8,9 *	1-6,11, 12	
			TECHNICAL FIELDS SEARCHED (Int.CI.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 31 October 2001	Examiner Derz, T
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 11 2368

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

31-10-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9940151 A	12-08-1999	WO 9940151 A1	12-08-1999
		EP 1044240 A1	18-10-2000
		NO 20003821 A	26-07-2000
WO 9924479 A	20-05-1999	AU 1035799 A	31-05-1999
		BR 9814854 A	03-10-2000
		CN 1285851 T	28-02-2001
		EP 1028985 A1	23-08-2000
		WO 9924479 A1	20-05-1999
EP 0714923 A	05-06-1996	AU 705455 B2	20-05-1999
		AU 3790395 A	30-05-1996
		CA 2162946 A1	22-05-1996
		CN 1128767 A	14-08-1996
		DE 69517771 D1	10-08-2000
		DE 69517771 T2	23-11-2000
		EP 0714923 A1	05-06-1996
		JP 3002119 B2	24-01-2000
		JP 8198922 A	06-08-1996
		US 5703172 A	30-12-1997
		US 5804665 A	08-09-1998
		JP 3034452 B2	17-04-2000
		JP 8198923 A	06-08-1996
DE 29722949 U	26-02-1998	DE 29722949 U1	26-02-1998
EP 0177961 A	16-04-1986	AT 381110 A	25-08-1986
		AT 322984 A	15-01-1986
		CS 8507292 A3	18-11-1992
		DE 3443599 A1	17-04-1986
		DE 3561399 D1	18-02-1988
		EP 0177961 A2	16-04-1986
		HU 40152 A2	28-11-1986
		SK 277920 B6	09-08-1995
US 6051638 A	18-04-2000	CA 2199556 A1	10-09-1998
WO 9935430 A	15-07-1999	DE 19758124 C1	18-11-1999
		AU 2417499 A	26-07-1999
		CN 1285904 T	28-02-2001
		WO 9935430 A1	15-07-1999
		EP 1042629 A1	11-10-2000
EP 0790262 A	20-08-1997	AU 717990 B2	06-04-2000
		AU 6838296 A	19-03-1997
		DE 69608240 D1	15-06-2000

FPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 11 2368

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

31-10-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0790262 A	DE	69608240 T2	23-11-2000
	EP	0790262 A1	20-08-1997
	US	6005034 A	21-12-1999
	CA	2203876 A1	06-03-1997
	WO	9708218 A1	06-03-1997
	TW	416962 B	01-01-2001

PUB-NO: EP001260546A1
DOCUMENT-IDENTIFIER: EP 1260546 A1
TITLE: Polyolefin multilayer pipe
PUBN-DATE: November 27, 2002

ASSIGNEE-INFORMATION:

NAME	COUNTRY
BOREALIS TECH OY	FI

APPL-NO: EP01112368
APPL-DATE: May 21, 2001

PRIORITY-DATA: EP01112368A (May 21, 2001)

INT-CL (IPC): C08K005/00 , C08L023/10 ,
F16L009/12 , F16L009/127 ,
F16L009/133 , B32B001/08 ,
B32B027/32 , C08F110/06 ,
C08F297/08 , C08F010/06

EUR-CL (EPC): B32B001/08 , B32B027/32 ,
C08K005/00 , F16L009/12 ,
F16L009/127 , F16L009/133

ABSTRACT:

CHG DATE=20030114 STATUS=O> Polyolefin multilayer pipes consisting at least one of the layers of a beta -nucleated propylene homopolymer and/or beta -nucleated copolymers from 90.0 to 99.9 % by weight of propylene and 0.1 to 10.0 % by

weight of alpha -olefins. The pipes are to be classified in ring stiffness class ≥ 4 . The pipes are suitable for non pressure pipe applications, preferably for outdoor use, for above as well as underground drainage and sewerage pipe systems, surface water pipes, pipes for cable protection, pipes for cold climate conditions and for indoor use, soil and waste water pipes.